

3M Novec™ 7200

Engineered Fluid

Introduction

3M™ Novec™ 7200 Engineered Fluid, ethoxy-nonafluorobutane (C₄F₉OC₂H₅), is a clear, colorless and low-odor fluid intended to replace ozone-depleting substances (ODSs), compounds with high global warming potential (GWP) and chlorinated materials in many applications. Its physical properties are compared with several other ODS replacement fluid candidates in Tables 1 and 2.

This proprietary fluid has zero ozone depletion potential and other favorable environmental properties (see Table 2). It is low in toxicity, with a time-weighted average exposure guideline of 200 ppm (eight hour average).

Novec 7200 fluid has a higher boiling point than most CFCs, HCFCs and HFCs, reducing evaporative losses. The low surface tension and low viscosity of Novec 7200 fluid make it ideal for use in vapor degreasing and cold cleaning applications. In addition, its chemical and thermal stability, nonflammability and low toxicity make it useful for other industrial applications such as specialty solvent and heat transfer applications (see below).

Typical Applications

- Cold cleaner (flex circuits, wipe solvent)
- Cleaning and rinsing agent for vapor degreasing
 - Light-duty cleaning (neat)–particulates, fluorolubes, light oils, fluoropolymers
- Lubricant carrier
 - Fluorocarbons
 - Hydrocarbons
 - Silicones
- Specialty solvents, dispersion medium, reaction medium, extraction solvent
- Spray contact cleaner
- CFC, HCFC, HFC and PFC replacement agent
- Heat Transfer Fluid
 - See 3M Electronic Materials “Thermal Management Fluids and Services” brochure.

Material Description

Ingredients

Ethoxy-nonafluorobutane¹

Appearance

Non-volatile residue (NVR)

Novec 7200

99.0% minimum

Clear, colorless

1.0 ppm maximum

¹ Novec 7200 fluid (C₄F₉OC₂H₅) consists of two inseparable isomers with essentially identical properties. These are (CF₃)₂CFCF₂OC₂H₅ (CAS No. 163702-06-5) and CF₃CF₂CF₂CF₂OC₂H₅ (CAS No. 163702-05-4).

**Typical Physical
 Properties
 – Table 1**

Data compiled
 from published
 information

Not for
 specification
 purposes

Properties

Novac 7200

Formula	C ₄ F ₉ OC ₂ H ₅
Molecular Wt.	264
Boiling Pt. °C	76
Freeze Pt. °C	-138
Liquid Density ¹	1.43
Surface Tension ²	13.6
Solubility of Solvent in Water ³	<20
Solubility of Water in Solvent ³	92
Vapor Pressure ⁴	109
Viscosity ⁵	0.61
Heat of Vaporization ⁶	30
Specific Heat ⁷	0.29

¹ g/ml @ 25°C ² dynes/cm @ 25°C ³ ppm by weight ⁴ mm Hg @ 25°C ⁵ cps @ 25°C
⁶ cal/g @ boiling point ⁷ cal/g °C @ 25°C

**Environmental
 and Exposure
 Guidelines
 – Table 2**

Data compiled
 from published
 information

Not for
 specification
 purposes

Properties

Novac 7200

Ozone Depletion Potential ¹ —ODP	0.00
Global Warming Potential ² —GWP	55
Atmospheric Lifetime—ALT (yrs)	0.77
Flashpoint	None
Flammability Range in Air	2.4–12.4%
Exposure Guidelines (8 hr. time-weighted average)	200 ppm
Acute Toxicity (4 hr. LC ₅₀ [Rat])	>92,000 ppm

¹ CFC-11 = 1.0 ² GWP–100 year Integration Time Horizon (ITH) *Note: HCFC-225 ca/cb ratio is 45/55*

	Novec 7100	HFC-4310mee	HCFC-225 ca/cb
	$C_4F_9OCH_3$	$C_5H_2F_{10}$	$C_3Cl_2HF_5$
	250	252	203
	61	54	54
	-135	-80	-131
	1.52	1.58	1.55
	13.6	14.1	16.2
	12	140	330
	95	490	310
	202	226	290
	0.61	0.67	0.59
	30	31	34.6
	0.28	0.27	0.24

	Novec 7100	HFC-4310mee	HCFC-225 ca/cb
	0.00	0.00	0.03
	320	1700	180/620
	4.1	17.1	2.1–6.2
	None	None	None
	None	None	None
	750 ppm	200 ppm	50 ppm
	>100,000 ppm	11,000 ppm	37,000 ppm

Vapor Pressure and Density

The variation of vapor pressure and density with temperature for 3M™ Novec™ 7200 Engineered Fluid can be calculated using the following formulas:

$$\text{Vapor Pressure: } \ln P = 22.289 - 3752.1 [1/(t+273)]$$

$$\text{Density: } D = 1.4811 - 0.0023026t$$

P = Vapor Pressure in Pascals

t = Temperature in °C

D = Density in g/ml

Environmental, Health and Safety

Before using this product, please read the current product Material Safety Data Sheet (available through your 3M sales or technical service representative) and the precautionary statement on the product package. Follow all applicable precautions and directions.

Novec 7200 fluid is nonflammable and does not exhibit flammability characteristics under normal operating and storage conditions. This fluid is highly resistant to thermal breakdown and hydrolysis in storage and during use. Recommended handling procedures are provided in the pertinent Material Safety Data Sheet which is available from your local 3M representative upon request.

Regulatory Status

3M™ Novec™ 7200 Engineered Fluid has been accepted for commercial use by regulatory agencies in the United States, Europe, Canada, Japan, Korea and the Philippines (less than 2,000 lbs/yr). The components of Novec 7200 fluid have been nominated to China's draft chemical inventory.

Novec 7200 fluid has been approved under the Significant New Alternatives Policy (SNAP) of the U.S. EPA. Novec 7200 fluid has been excluded by the U.S. EPA from the definition of a VOC on the basis that this compound has negligible contribution to tropospheric ozone formation. In addition, the South Coast Air Quality Management District (SCAQMD) has certified Novec 7200 fluid as a Clean Air Solvent.

The components of Novec 7200 fluid are not on any regulated lists.

Contact your local 3M representative regarding the regulatory status of Novec 7200 fluid in other countries.

Toxicity Profile

The toxicological testing completed on Novec 7200 fluid shows the overall toxicity is low. The material is minimally irritating to the eyes, non-irritating to the skin and is not a mutagen. This material is rated "practically non-toxic" through inhalation. A twenty-eight day inhalation study has helped establish a recommended exposure guideline of 200 ppm for an eight-hour average worker exposure per day.

Toxicological Test Results

Properties	Novec 7200
Acute Lethal Inhalation Concentration	> 92,000 ppm (4 hour)
Oral	Practically non-toxic (>5g/kg)
Eye Irritation	Minimally irritating
Skin Irritation	Non-irritating
Skin Sensitization	Not a skin sensitizer
Inhalation (28 day study)	200 ppm exposure guideline ¹ Detailed results are available
Developmental Toxicity	Detailed results are available
Mutagenicity	Not a mutagen
Cardiac Sensitization	No signs at exposure up to 20,000 ppm
Ecotoxicity Testing	Complete—low aquatic toxicity

¹Exposure Guideline set by the 3M Medical Department

Materials Compatibility

Continuous Exposure

3M™ Novec™ 7200 Engineered Fluid is compatible with most metals and hard polymers. Soft and elastomeric materials should be limited to compounds that contain the least amount of extractable plasticizer. 3M technical service engineers can suggest appropriate compounds and assist with material compatibility tests.

Non-Continuous Exposure

Short-term testing of Novec 7200 fluid demonstrates compatibility, after one hour exposure at boiling temperature, with a wide range of metals, plastics and elastomers, similar to the performance of perfluorinated liquids. Good short-term compatibility with particularly sensitive plastics such as polycarbonate and PMMA indicates utility in cleaning of assemblies containing many composite materials.

As with most fluorinated liquids, Novec 7200 fluid will absorb into fluorinated plastics and elastomers over longer exposures.

Short Term Exposure Compatibility

Metals	Plastics	Elastomers
Aluminum	Acrylic (PMMA)	Butyl Rubber
Copper	Polyethylene	Natural Rubber
Carbon Steel	Polypropylene	Nitrile Rubber
302 Stainless Steel	Polycarbonate	EPDM
Brass	Polyester	
Molybdenum	Epoxy	
Tantalum	PET	
Tungsten	Phenolic	
Cu/Be Alloy C172	ABS	
Mg Alloy AZ32B		

Exceptions: Some swelling of PTFE and Silicone Rubber. Some surface oxidation of copper during heat aging.

Recycle and Disposal Options

Used Fluid Return Program

3M offers a program for free* pickup and return of used 3M specialty fluids in the U.S. through Safety-Kleen Corp. A pre-negotiated handling agreement between users and this service provider offers users broad protection against future liability for used 3M product. The fluid return program is covered by independent third-party financial and environmental audits of treatment, storage and disposal facilities. Necessary documentation is provided. A minimum of 30 gallons of used 3M specialty fluid is required for participation in this free program.*

Safety-Kleen Corp. has a network of 156 branch service centers in the U.S. This large fleet will provide timely, economical fluid disposal service.

For additional information on the 3M Used Fluid Return Program, contact Safety-Kleen at this toll-free line: 1.888.932.2731. Contact your local 3M representative for fluid return programs outside the U.S.

* Must have a 30 or more gallon purchase to participate in the 3M paid program. Used product of 5-30 gallons can be returned through Safety-Kleen at the user's expense.

Environmental Policy

3M will continue to recognize and exercise its responsibility to prevent pollution at the source wherever and whenever possible; develop products that will have a minimal effect on the environment; conserve natural resources through the use of reclamation and other appropriate methods; assure that its facilities and products meet and sustain the regulations of all federal, state and local environmental agencies; assist, wherever possible, governmental agencies and other official organizations engaged in environmental activities.

Packaging and Availability

3M™ Novec™ 7200 Engineered Fluid may be ordered in the following container sizes:

- 55-gallon drum; 5-gallon pail; 1-gallon pail
- 4-ounce samples for limited or preliminary test work are available

Resources

3M™ Novec™ Engineered Fluids are supported by global sales, technical and customer service resources, with fully-staffed technical service laboratories in the U.S., Europe, Japan, Latin America and Southeast Asia. Users benefit from 3M's broad technology base and continuing attention to product development, performance, safety and environmental issues.

For additional technical information on 3M™ Novec™ 7200 Engineered Fluid in the United States, call 3M Customer Service, **800 810 8513**.

For information on additional 3M fluids, coatings and other chemical products for the electronics industry, visit our web site at:

www.3M.com/electronics

Product Use: All statements, technical information and recommendations contained in this document are based on tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy: Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. **3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.** User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability: Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



3M Electronics

Building 21-1W-10
900 Bush Avenue
St. Paul, MN 55106

www.3M.com/electronics

3M is a trademark of 3M Company.
Used under license by 3M subsidiaries and affiliates.

Issued: 8/05

© 2005 3M

5045(HB)
98-0212-2374-2